StaBrite™

DRY BRIGHT FLOOR COATING

StaBright is an excellent, low maintenance coating with outstanding resistance to scuffs, scratches, black heel marks and detergent scrubbings.

DIRECTIONS

Read all directions and Safety Data Sheets (SDS) before using.

1. For a floor that has been stripped, properly neutralized, rinsed and allowed to dry thoroughly, apply 5-6 thin coats using a clean synthetic mop. Allow the floor to dry thoroughly between coats and prior to burnishing.
2. Optional: Apply 2 thin coats of floor sealer for old or porous floors or for high traffic areas, then apply 4 coats of finish.
3. For a floor that has been deep scrubbed and allowed to dry thoroughly, apply 1-2 thin coats using a clean synthetic mop. Allow floor to dry thoroughly between coats and prior to burnishing.

PRODUCT INFO

Product Code	130FS	130FSE	130MPE	130DR
Volume	2.50 US gallons	10 liters	4 liters	55 US gallons
Shipping Package	2 x 2.5 gallons	2 x 10 liters	4 x 4 liters	per unit
Pallet Quantity	48	48	48	4

SURFACES

VCT

TECHNICAL DATA

Description	Polymer emulsion
Appearance	Milky white
Specular Gloss (60°) ASTM D1455-87 (2008)	>85
Viscosity (Brookfield) @ 68°F (20°C)	<10 centipoise
Coverage Rate	2500 to 3000 ft²/gal 61 to 74 m²/liter
Dry Time	About 30 minutes
Removability ASTM D1792-06	Excellent
VOC 40 CFR Part 59 Subpart C	0.01%
Non-Volatile Solids ASTM D2834-95 (2008)	20%
Fragrance	Slight ammoniacal
Slip Resistence ULTM410	Meets requirements
Shelf Life ASTM D1791-93 (2008)	1 year
Density ASTM D1475-98 (2008)	8.6 lb/gal @ 68°F 1.03 kg/L @ 20°C
Detergent Resistence ASTM D3207-92 (2008)	Excellent
Freeze/Thaw ASTM D3209-93 (2008)	Passes 3 cycles
Container	2.5 US gal/9.5 L (FS packaging) 2.64 US gal/10 L (FSE packaging) 1.06 US gal/4 L (MPE packaging) 55 US gal/208 L (DR packaging)

Floor Coating and Finishing materials as to slip resistance only. 42E6

SDS sheets available for download at pioneereclipse.com.

130_PDS 03/2016

© 2016 Amano Pioneer Eclipse Corporation® • 1 Eclipse Road • PO Box 909 • Sparta, NC 28675 USA

1-800-367-3550 • 1-336-372-8080 • Fax: 1-336-372-2895 • www.pioneereclipse.com